

Innovation Breakthrough

Process Free Plate

- Eco-friendly
- No processor chemical developing
- No investment on processor and space
- No more processor clean and maintenance
- Cost savings of developer, water, electricity and chemical disposal



TOP HIGH IMAGE

We Promise, We Do!

No. 20, Jiukuang 2nd St., Daliao Dist.,
Kaohsiung City, Taiwan 83100
Tel : +886(7)787-7690
Fax: +886(7)787-1354



T-20

Process Free Plate

Plate	Non-ablative thermal negative short to medium-run plate.
Gauge	0.15 / 0.30 mm (0.20 / 0.24mm on request)
Spectra Sensitivity	800 - 850 nm
Laser Energy	110 - 150 mJ/cm ² (Recommend 135 mJ/cm ²)
Resolution	1% - 99% @ 200 lpi
Runlength	Sheet-fed: 150,000 / Web-fed: 200,000 impressions (Actual runlength may vary according to press, ink and paper conditions.)
Safelight	Up to 1 hour under white light Up to 12 hours under yellow light
Shelf life	12 months under recommended storage conditions
Packaging	Available in all standard formats, including bulk and Auto Pallet Loader (APL) formats.
Storage	Unopened plate packs should be stored flat and away from excessive cold, heat and humidity. Store in a controlled environment of below 25°C and 50% RH, non-condensing.
Handling	Handle with gloves. Once opened, suggest to use within 3 days; unused plates should be sealed with tape and kept away from light for storage.



TOP HIGH IMAGE